











JEMBER – trousers							
<p>Description</p> <ul style="list-style-type: none"> • 2 wide front pockets, • double back pocket with flap closed with snap, • fabric with high elastic perception, • hammer loop, • knee and leg ergonomic design, • left side pocket with double opening (with snap and zip closure), • right side pocket closed with snap, • availability in single bag (V567-0) and / or in box (V567-1). 							
<p>Maintenance</p> <p>Maximum wash temperature: 40 °C; Do not bleach ; Dry clean with solvents on point F plus Tetrachloroethylene; Tumble drying possible - Drying at lower temperature; Drying in the shade; Ironing at low temperature (max 110 °C).</p> <div style="display: flex; justify-content: space-around; align-items: center;">       </div>	<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 30%;">Item</td> <td>V567-0-00 KHAKI/BLACK V567-0-01 AVION/ BLACK V567-0-02 NAVY/ BLACK V567-0-03 CLAY BROWN/ BLACK V567-0-04 ANTHRACITE/BLACK V567-0-05 BLACK/BLACK</td> </tr> <tr> <td>Standards:</td> <td>EN ISO 13688:2013 </td> </tr> <tr> <td>Sizes Sizes Long Sizes Short</td> <td>44 – 64 L 33 – L 38 S 36 – S 41</td> </tr> </table>	Item	V567-0-00 KHAKI/BLACK V567-0-01 AVION/ BLACK V567-0-02 NAVY/ BLACK V567-0-03 CLAY BROWN/ BLACK V567-0-04 ANTHRACITE/BLACK V567-0-05 BLACK/BLACK	Standards:	EN ISO 13688:2013 	Sizes Sizes Long Sizes Short	44 – 64 L 33 – L 38 S 36 – S 41
Item	V567-0-00 KHAKI/BLACK V567-0-01 AVION/ BLACK V567-0-02 NAVY/ BLACK V567-0-03 CLAY BROWN/ BLACK V567-0-04 ANTHRACITE/BLACK V567-0-05 BLACK/BLACK						
Standards:	EN ISO 13688:2013 						
Sizes Sizes Long Sizes Short	44 – 64 L 33 – L 38 S 36 – S 41						

SAFETY TECHNICAL SPECIFICATIONS

	Test method	Description	Cofra result	Minimum requirement / range
Background fabric	EN ISO 1833-1977, SECTION 10	Composition:	60% cotton 37% polyester 3% elastane	
	EN ISO 12127:1996	Fabric mass per unit area	245 g/m ²	
	EN ISO 13688:2013 4.2 (ISO 3071)	The pH's determination from the watery extract	OEKO-TEX [®] Standard 100	3,5 ≤pH≤ 9,5
	EN ISO 13688:2013 4.2 (EN 14362-1)	Search of the aromatic and carcinogenic amines	OEKO-TEX [®] Standard 100	≤30 ppm
	EN ISO 13688:2013 5.3 (ISO 5077)	Dimensional change to washing (40°C)	warp: -1.3% weft: 0.9%	±3%

ISO 105-C06	Colour fastness to Laundering at 40°C			1-5
	<i>Colour change</i>	4-5		
	<i>Staining:</i>			
	diacetate	4-5		
	cotton	4-5		
	nylon	4-5		
	polyester	4-5		
	acrylic	4-5		
	wool	4-5		
ISO 105 D01	Colour fastness to to dry cleaning			1-5
	<i>Colour change</i>	4-5		
	<i>Staining:</i>			
	diacetate	4-5		
	cotton	4-5		
	nylon	4-5		
	polyester	4-5		
	acrylic	4-5		
	wool	4-5		
ISO 105 E04	Colour fastness to perspiration	Acidic	Alkaline	1-5
	<i>Colour change</i>	4-5	4-5	
	<i>Staining:</i>			
	diacetate	4-5	4-5	
	cotton	4-5	4-5	
	nylon	4-5	4-5	
	polyester	4-5	4-5	
	acrylic	4-5	4-5	
	wool	4-5	4-5	
ISO 105-X12	Colour fastness to rubbing	Dry: 4-5		1-5
		Wet: 3-4		
EN ISO 105-X11	Colour fastness to hot pressing (110°C);			1-5
	<i>Colour change</i>	Dry: 4-5		
		Wet: 4-5		
ISO 105-B02	Colour fastness to light			1-5
	<i>Colour change:</i>	4		
EN ISO 13934-1	Tensile strength	warp: 1600 N		
		weft: 6 20 N		
EN ISO 13937-2	Tear strenght	warp: 44 N		
		weft: 51 N		
ISO 12947-2	Determination of the abrasion resistance of fabrics by the Martindale method	>30000 cycles		