

Walklander - trousers

description • knee and leg ergonomic design • reinforced crotch (Walklander) • wide front pockets • coin pocket • 2 back pockets, one of them with flap • side pocket • rule pocket • hammer loop • pen pocket • adjustable waist • YKK® zip

maintenance maximum wash temperature: 60°C - do not bleach - dry cleaning allowed - drying in tumble dryer not allowed - medium iron temperature: 110°C



WALKLANDER - DRILL



Item	V014-0-00 khaki/black V014-0-01 grey/black V014-0-02 navy/black V014-0-03 brown/black V014-0-04 anthracite/black V014-0-05 black/black
Standards	EN ISO 13688:2013  Tested for harmful substances according to Oeko-Tex® Standard 100
Sizes	44 – 64 / UK 30-46 (RIGHT FIT S52-S58 / L48-L54)

SAFETY TECHNICAL SPECIFICATIONS

<i>Test method</i>	<i>description</i>	<i>Cofra result</i>	<i>minimum requirement / range</i>
Background fabric EN ISO 1833-1977, SECTION 10	Composition: Cotton/polyester	60 / 40 %	
	Weave: twill 2/2	Warp : 35 [yarn/cm] Weft : 20 [yarn/cm]	
EN ISO 12127:1996	Weight per unit area	290 gr/sqm	
EN ISO 105-C06 E2S: 1994	Colour fastness to washes (60°C)	Colour change : 3	1 - 5
		Staining : 4 - 5	
EN ISO 105 D01:1993	Colour fastness to dry cleaning	Colour change : 4	1 - 5
ISO 5077:1994, ISO 6330: 1994	Dimensional change to washes (60°C)	Warp: - 0.2 %	Max 3 %
		Weft: - 0.3 %	Max 3 %
ISO 105X12: 2001	Colour fastness to rubbing	Dry: 4 - 5	1 - 5
		Wet: 3 - 4	1 - 5
EN ISO 105 B02: 1993, METODO 3	Colour fastness to light	3 - 4	1 - 5
ISO 105-N01:1993	Colour fastness to bleaching	Colour change : 2-3	1 - 5
EN ISO 13934-2: 1999	Tensile strength	Warp: 1000 N	400 N
		Weft: 610 N	400 N
EN340/03 paragraph 4.2 (EN 1413)	The PH's determination from the watery extract	PH 7.0	3,5<PH≤9,5
EN340/03 paragraph 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm